



writeMAGNETIC (dry erase wallcovering)

technical data sheet

- Total Weight:** 54.00 oz / sq yd or 24.00 oz / lin ft
 - Base Film Weight:** 51.25 oz / sq yd
 - Backing Weight:** 1.80 oz / sq yd
 - Top Film Weight:** .95 oz / sq yd
 - Backing:** 100% Polyester
 - Laminate Thickness:** 1 mil
 - Total Thickness:** 30 mils
 - Widths:** 48"
 - Flame Resistance:** Class A (ASTM E-84)
 - Tensile Strength:** 275 x 208 lbs (ASTM D 5034)
 - Tear Strength:** 11.8 x 7.2 lbs (ASTM D 2261)
 - Solvent Resistance:** 1,000 Double rubs w/ MEK (ASTM D 4752)
 - Colorfastness:** Class 4.5 - 5 at 200 AFU (AATCC 16E)
 - Abrasion Resistance:** 20,000 Double Rubs - Wyzenbeek (ASTM D 3597)
- Note:** For best results, rare earth or Neodymium magnets are recommended for WriteMagnetic.